



Dimensions

Date 8/27/2003
Test Method ASTM C140-02a - Standard Test Methods for Sampling and Testing concrete Masonry Units and Related Units
Sample Type Whole units
Equipment Mitutoyo Digital Calipers CD-18 SN 7003817 Intertek ID P52639
Starrett Delfection Gauge SN 013172564 Intertek ID D 2673

	Max Length	Max Width	Max Thickness	Max Back Face Deviation	Max Possible Area
Measured Values	(mm) 635	(mm) 248	(mm) 56	(mm) 13	(m ²) 0.16
CCMC 07483 (maximum) Status	900 Pass	900 Pass	70 Pass	3 Fail	0.26 Pass

